

MATERIAL SPECIFICATIONS



.

LOAD TABLES

Refer to Trim Pamphlet for Material Availability

TETON STEEL 7.2 ULTRA BOX PANEL

26 Gauge (0).0181"), Fy = 60 ksi, Fu = 61.5 ksi								
SPAN	LOAD TYPE	SPAN IN FEET							
TYPE		3.0	4.0	5.0	6.0	7.0	8.0	9.0	
1-span	NEGATIVE WIND LOAD	237.61	133.66	85.54	59.40	43.64	33.41	26.40	
	LIVE LOAD/DEFLECTION	162.95	103.02	52.75	30.53	19.22	12.88	9.04	
2-span	NEGATIVE WIND LOAD	222.59	136.44	91.38	65.16	48.68	37.69	30.01	
	LIVE LOAD/DEFLECTION	143.95	107.96	79.83	56.57	42.08	32.49	25.82	
3-span	NEGATIVE WIND LOAD	258.47	162.17	110.20	79.32	59.63	46.36	37.03	
	LIVE LOAD/DEFLECTION	163.58	122.69	97.08	64.84	40.83	27.35	19.21	
4 enan	NEGATIVE WIND LOAD	247.30	153.99	104.13	74.72	56.05	43.52	34.72	
4-span	LIVE LOAD/DEFLECTION	157.45	118.09	91.48	65.14	44.07	29.52	20.74	
24 Gauge (0.0223"), Fy = 50 ksi, Fu = 60 ksi									
SPAN		SPAN IN FEET							
TYPE	EGAD TIFE	3.0	4.0	5.0	6.0	7.0	8.0	9.0	
1-span	NEGATIVE WIND LOAD	251.48	141.46	90.53	62.87	46.19	35.36	27.94	
	LIVE LOAD/DEFLECTION	202.14	135.78	69.52	40.23	25.33	16.97	11.92	
2-span	NEGATIVE WIND LOAD	253.79	147.73	96.14	67.39	49.79	38.27	30.31	
	LIVE LOAD/DEFLECTION	156.28	117.21	88.20	61.73	45.57	35.00	27.71	
3-span	NEGATIVE WIND LOAD	307.17	181.07	118.61	83.46	61.81	47.58	37.73	
	LIVE LOAD/DEFLECTION	177.59	133.19	106.55	76.57	53.77	36.02	25.30	
4 enan	NEGATIVE WIND LOAD	289.91	170.16	111.21	78.15	57.83	44.49	35.27	
4.enan	HEOMINE HIND EOM								
4-span	LIVE LOAD/DEFLECTION	170.93	128.19	102.17	71.66	52.97	38.84	27.28	

22 Gauge (0.0286"), Fy = 50 ksi, Fu = 60 ksi										
SPAN	AN LOAD TYPE	SPAN IN FEET								
TYPE		3.0	4.0	5.0	6.0	7.0	8.0	9.0		
1-span	NEGATIVE WIND LOAD	346.31	194.80	124.67	86.58	63.61	48.70	38.48		
	LIVE LOAD/DEFLECTION	322.96	181.52	92.94	53.78	33.87	22.69	15.94		
2-span	NEGATIVE WIND LOAD	357.18	205.97	133.40	93.26	68.79	52.81	41.80		
	LIVE LOAD/DEFLECTION	199.38	149.54	119.63	85.47	63.01	48.35	38.26		
3-span	NEGATIVE WIND LOAD	435.96	253.83	165.20	115.80	85.57	65.76	52.09		
	LIVE LOAD/DEFLECTION	226.57	169.93	135.94	106.25	71.31	47.77	33.55		
4-span	NEGATIVE WIND LOAD	410.29	238.09	154.70	108.33	80.00	61.46	48.67		
	LIVE LOAD/DEFLECTION	218.07	163.56	130.84	99.36	73.31	51.25	35.99		

1. Strength Calculations based on the 2012 AISI Standard "North American Specification for the Design of Cold-formed Steel Structural

Allowable loads are applicable for uniform loading and spans without overha
 LIVE LOAD/DEFLECTION load capacities are for those loads that push the pane

3. LIVE LOAD/DEFLECTION load capacities are for those loads that push the panel against its support. The applicable limit states are flexure, shear, combined shear and flexure, web crippling at end and interior supports, and a deflection limit of L/180 under strength-level loads.

4. NEGATIVE WIND LOAD capacities are for those loads that pull the panel away from its supports. The applicable limit states are flexure, shear, combined shear and flexure, and a deflection limit of L/60 under 10-year wind loading.
5. Panel pullover and Screw pullout capacity must be checked separately using the screws employed for each particular application when

utilizing this load chart. 6. Effective yield strength has been determined in accordance with section A2.3.2 of the 2012 NAS specification. 7. The use of any accessories other than those provided by the manufacturer may damage panels, void all warranties and will void all

7. The use of any accessories other than those provided by the manufacturer may damage panels, void all warranties and will void al engineering data. 8. This material is subject to change without notice please contact Teton Steel for most current data.

The Engineering data contained herein is for the expressed use of customers and design professionals. Along with

recommended that the design professional have a copy of the most current version of the **North American Specification for the Design of Cold-Formed Steel Structural Members** published by the American Iron and Steel Institute to facilitate design. The Specification contains the design criteria for cold formed steel components. Along with the Specification, the designer should reference the most current building code applicable to the project jobsite in order to determine environmental loads. If further information or guidance regarding cold-formed design practices is desired, please contact the manufacturer.



Available Gauges: 22, 24 & 26

Weight: 5.00lbs/LnFt (22), 4.00lbs/LnFt (24), 3.00lbs/LnFt (26)

Substrate: AZ-50, Grade D, 50,000ksi

Available Materials: Painted, Galvalume, ReziBond[®], Core Ten[™]

Paint Systems: Durapon70[™] PVDF, ULTRA CLAD[™] Kynar500[®]/Hynar500[®]

Warranties: Durapon70[™] PVDF – 35 year ULTRA-CLAD[™] - 35 year Zincalume[®] AZ50 – 20 year

Minimum Slope: 1:12 with Bead Seal and Stitch Screws installed 1'0" up the panel at all side laps.



• UL 580 Wind Uplift (Class 90)

• UL 2218 Class 4 Hail Impact

• UL 790 Class A Fire Rating

APPLICATION DETAILS

Fastener Guide:

#10 Woodfast screws are designed for use with dimensional lumber

#14 Wafer screws are designed for use with plywood sheeting, OSB, and wafer wood (7/16" minimum thickness)

#12 Tek Screws are designed to be used with structural steel up to 3/16" in thickness

Fastener Application:

Screws are to be applied in the middle of every other trough and then on both sides of the rib at each overlap of the panels, installed not more than 5'0" up the panel. At eaves and panel end laps, use a double screw pattern, and fasten into the middle of every trough. On all roofing applications, Mastic Tape must be applied between every panel at the side lap with Stitch Screws installed every 1'0" up the panel.

Please Note: It is the responsibility of the builder to ensure that purlins are adequately spaced to meet specific engineering requirements.

Teton Steel is neither partially or solely responsible for improper installation or defects as a result of installation

2380 E 24th N. | Idaho Falls, Idaho 83401 | 208.528.6600